

Scapa 9080S

Paper Masking Adhesive Tape - 80°C, Indoor Use

DESCRIPTION

Scapa 9080S is 125 µm semi crepe tape coated with a solvent rubber adhesive system, recommended for all general purpose indoor 80°C masking applications

APPLICATIONS

- Suitable for all general purpose 80°C indoor bonding, holding, sealing and masking applications.
- Industrial EOM premium masking tape.
- Premium masking tape for building and painters masking applications for indoor use.
- Automotive aftermarket masking tape with short term oven baking resistance.

PRODUCT BENEFITS

- Continuous temperature resistance: +80°C.
- Resistant to oven baking.
- Resistant to chemicals, lacquers and solvents.
- No staining.
- Good shear and holding strength.
- Flexible and easy to use
- Good peel adhesion.
- Excellent paint flake resistance.
- Smooth and controlled unwind.
- Clean and easy removal.

TECHNICAL PROPERTIES

Technical Property	Nominal Value	Unit	Test Method
Adhesion to Steel	2.3	N/cm	AFERA 5001
Elongation at Break	10	%	AFERA 5004
Tensile Strength	32	N/cm	AFERA 5004
Total Thickness	125	µm	AFERA 5006

STANDARD PRESENTATIONS

- Colours: Natural
- Packaging: Concertina
- Roll Length: 50 metres
- Roll Length: 76mm Scapa or Barnier branded cardboard core
- Roll Width: 19, 25, 30, 38 and 50mm

RECOMMENDATIONS

The rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Storage temperature between +10°C and +30°C. Under these conditions, the storage life of the tape in a temperate climate should not exceed 12 months.

Surfaces should be clean, dry and free of dust, grease, oil or other contaminants.

Scapa masking tapes are not suitable for outdoor exposure and should not be submitted to prolonged periods of sunlight, as tapes may become difficult to remove. Clean removal may also vary with surface type, lacquers, primers and paints nature as well as the temperature of the surface at removal. For best results, remove the tape as soon as possible after applying the paints pulling it slowly at a 90° angle with constant speed