



Scapa UA202

Acrylic Transfer Adhesive - Medium Firm, 2.0 mils

DESCRIPTION

Scapa UA202 is an acrylic transfer adhesive, supplied with a 60# kraft release liner.

APPLICATIONS

- General bonding and mounting.
- Application of decorative parts.
- Nameplates and faceplates.

PRODUCT BENEFITS

- Exhibiting good tack and peel along with moderate shear and heat resistance.
- Good chemical and plasticizer resistance.
- Adhesive is clear and has excellent UV and humidity resistance.
- Performs well over a wide temperature range and offers high peel strength.
- Laminates well to a variety of substrates including metals, plastics, and foams.

TECHNICAL PROPERTIES

Technical Property	Nominal Value	Unit	Test Method
Adhesive Colour	Clear	-	-
Adhesive Thickness	2.0 (.051)	Mils (mm)	-
Liner Thickness (50# tan Kraft)	>900	Min	-
Liner Thickness (60# Kraft)	3.5 (.089)	Mils (mm)	-
Peel Adhesion	82 (23)	Oz/Inch (N/25mm)	PSTC 101 Mod. Initial to S.S. (20 min. @ RT)

STANDARD PRESENTATIONS

RECOMMENDATIONS

Application to Primary Surface:

Unwind adhesive film or tape and apply the adhesive side to the mounting surface. Apply firm pressure. Recommended application temperature to achieve best results is 65°F (18°C) or above. Proper bonding may not occur unless adhesive and surface material are both at 65°F (18°C) or above.

Application to Secondary Surface:

Peel off the protective release liner and apply the adhesive side to the desired surface. Apply firm pressure. Recommended application temperature to achieve best results is 65°F (18°C) or above. Proper bonding may not occur unless adhesive and surface material are both at 65°F (18°C) or above.

NOTE:

1. When applying pressure sensitive adhesive films to any surface, be sure that the surface is free from oil or other surface contaminants such as powder, dust, or release agents. Adhesive performance should be carefully checked when used on substrates containing plasticizers.
2. Shelf life is one year from date of shipment when stored in a cool dry place below 76°F (24°C). Rolls should be stored on end.